


Braid Reinforced Silicone Hose



- Open mesh polyester braiding incorporated within the walls of silicone tubing
- Raw materials meet FDA requirements per FDA 21 CFR 177.2600 for use with food contact surfaces
- Reusable — will withstand repeated sterilization[^]
- Translucent natural color for visual contact with the flow
- Able to resist extreme temperature variation: -99°F to 350°F
- Odorless, tasteless, and inert
- Excellent weatherability properties — resists U.V., ozone, gases, moisture, and extreme temperatures
- Offers far higher pressure capabilities than similarly-sized unreinforced silicone tubing
- Listed by the National Sanitation Foundation (NSF-51) for food equipment materials
- Free of BPA, latex and phthalates; RoHS compliant



Notes

The construction of SILBRADE enables silicone tubing to handle increased pressure applications. SILBRADE offers outstanding resistance to temperature extremes and is made from raw materials that meet FDA requirements.

The flexible design and construction of SILBRADE also allows excellent bend radii and permits installation in restricted spaces without impeding flow.

SILBRADE, a peroxide-cured product, contains no sulphur or other acid-producing chemicals thereby eliminating the possibility of staining, corroding, or deteriorating other materials it contacts. It is also resistant to ozone and U.V. over long time periods.

Care is recommended in the selection of fittings and clamps, as sharp barbed fittings or unlined metal clamps could tear into the hose wall and possibly cause a failure, especially at elevated pressures.

[^]SILBRADE may be low pressure steam sterilized in-line or autoclaved at up to 250°F in a normal autoclaving cycle. However, if exposed to repeated steam sterilization or long-term high temperature or pressure, silicone will eventually relax and become gummy. It should then be replaced.

SILBRADE is not recommended for implantable or in-body uses or for continuous steam applications.

Physical Properties**

Hardness, Shore A ±5 – Liner	70
Hardness, Shore A ±5 – Cover	60
Tensile Strength, psi	1460
Elongation at Break, %	320
Tear Resistance, Die B, ppi	100
Modulus at 100%, psi	415
Brittle Temperature, °F	-99
Maximum Operating Temperature, °F	350

**Values listed are typical for the material used in manufacture except where noted, apply to the hose liner except where noted, and are meant only as a guide to aid in design. Field testing should be performed to find the actual values for your application.

PART NO.	ID (IN.)	OD (IN.)	WALL (IN.)	STANDARD LENGTHS (FT.)	WORKING PSI AT 70°F	LBS. PER 100 FT.
290 0072	1/8	.365	.120	100	233	5
290 0149	3/16	.447	.130	100	216	7
290 0226	1/4	.520	.135	100	208	9
290 0303	5/16	.592	.140	100	183	11
290 0380	3/8	.655	.140	100	166	13
290 0457	1/2	.800	.150	50, 100	141	17
290 0534	5/8	.965	.170	50	116	23
290 0611	3/4	1.100	.175	50	91	28
290 0765	1	1.380	.190	50	75	36

Cut coils are available; charges apply — call for details.

Add length suffix to part number when ordering. Example: 100 ft. of 1/8" I.D. x .365" O.D. hose is part number 290 0072-100.

Working pressures are calculated from burst testing using a 3:1 safety factor. Application testing is recommended.

BOLD indicates the critical dimension for fittings application.



Recommended Fittings & Clamps

- Thermobarb® barbed fittings
- Oetiker® ear type clamps
- Kwik Clamp™ nylon double bond hose clamps
- Worm gear clamps

Custom Services

- Cut ■ Color
- Size ■ Hardness ■ Overbraid ■ And More

Call for more information: 800-506-3924 or 215-526-2300