

Platinum Cured Medical Grade Silicone Tubing

- Raw materials meet USP Class VI requirements
- Manufactured under good manufacturing procedures in a controlled environment
- Platinum cured for the highest degree of purity (least extractables)
- Reusable will withstand repeated sterilization[^]
- Translucent natural color for visual contact with the flow
- Applications include pharmaceutical, biomedical, health and beauty, food, and beverage handling
- Free of BPA, latex and phthalates
- RoHS compliant



PART NO.	ID (IN.)	OD (IN.)	WALL (IN.)
284 0404	.030	.160	.065
284 0677	1/16	1/8	1/32
284 0684	1/16	3/16	1/16
284 0978	1/8	1/4	1/16
284 0985	1/8	5/16	3/32
284 1174	3/16	5/16	1/16
284 1181	3/16	3/8	3/32
284 1272	1/4	3/8	1/16
284 1279	1/4	7/16	3/32
284 1286	1/4	1/2	1/8
284 1370	5/16	7/16	1/16
284 1377	5/16	1/2	3/32
284 1468	3/8	1/2	1/16
284 1475	3/8	9/16	3/32
284 1482	3/8	5/8	1/8
284 1580	1/2	3/4	1/8
284 1678	5/8	7/8	1/8
284 1692*	3/4	1	1/8
284 1685*	1	1-1/2	1/4

*Limited stock item; lead times and minimums may apply — call for details. Sold by standard coil length (50 ft); additional lengths may be available — call for details. Add length suffix to part number when ordering. Example: 50 ft. of .030" I.D. x .160" O.D. tubing is part number 284 0404-50. **BOLD** indicates the critical dimension for fittings application.

Recommended Fittings & Clamps

- Thermobarb® barbed fittings
- Oetiker® ear type clamps
- Kwik Clamp™ nylon double bond hose clamps
- Worm gear clamps







Notes

SILCON MED-X tubing is made under good manufacturing procedures and conforms to the biocompatibility requirements of USP Class VI.

SILCON MED-X's surface properties resist sticking and encrustation and will not support bacteria growth. The tubing is soft, pliable, and contains no plasticizers which could leach out, causing flow contamination or tube hardening.

Other sizes and 60A durometer material are also available — call for details.

Care is recommended in the selection and application of fittings and clamps as sharp barbed fittings or unlined metal clamps could tear into the wall.

Alf exposed to repeated steam sterilization or longterm high temperature or pressure, silicone will eventually relax and become gummy. It should then be replaced.

SILCON MED-X is supplied in individual, heat-sealed polybags and should be sterilized prior to use.

SILCON MED-X is not recommended for implantable or in-body uses or for continuous steam applications.

Physical Properties**

Hardness, Shore A ±5	50
Tensile Strength, psi	1348
Elongation at Break, %	900
Tear Resistance, Die B, ppi	250
Modulus at 100%, psi	190
Brittle Temperature, °F	-100
Maximum Operating Temperature, °F	400

**Values listed are typical for the material used in manufacture, except where noted, and are meant only as a guide to aid in design. Field testing should be performed to find the actual values for your application.