









Description:

Three-ply co-extruded material;

Foamed Low Density Polyethylene Core Between Two Solid Layers Of Low Density Polyethylene. Foamed Low Density Polyethylene

Original Date: 8 / 5 / 97

Revision Date: 2/14 98

SPECIFICATIONS

THICKNESS				AVAILABLE WEB WIDTH		
Minimum [in]	Maximum [in]	Deviation [in]	3	Minimum [in]	Maximum [in]	Deviation [in]
0.020	0.060	± 0.005	. 2	1.0	25.0	± 1/16
0.065	0.090	± 0.007	<u> </u>	1.0	9.0	± 1/16
0.095	0.125	± 0.010		1.0	9.0	± 1/16

DENSITY	Ţ.	Deviation
25 lbs / ft ³		$\pm 2 \text{ lbs / ft}^3$

AVAILABLE IN VARIOUS DENSITIES

F - 217 - 3 FDA Status: DMF 2434	F - 217 - 36 FDA Status: DMF 2434	F - 219 FDA Status: DMF 2434
(DENSITY)	(DENSITY)	(DENSITY)
$30 \pm 2 \mathrm{lb/ft}^3$	$36 \pm 2 lb/ft^3$	$19 \pm 1 \text{ lb/ft}^3$

CODE OF FEDERAL REGULATIONS COMPLIANCE:

21 CFR 177.1210:

Closures with sealing gaskets for food containers.

21 CFR 177.1520:

Olefin polymers.

21 CFR 178.2010

Antioxidants and or stabilizers for polymers

21 CFR 175 300 :

Resinous and polymeric coatings

PATENT NO .:

4107247 / 4206165

FDA STATUS:

The component materials of F-217 F-217-3, F-217-36, F-219 are listed under DMF 2434.

The aforementioned technical information and any recommendation are based on Tri-Seal's laboratory findings and are believed to be true and accurate, but we strongly recommend that our customers perform appropriate tests they feel necessary to insure the apatibility and stability of any given product with ours. Tri-Seal International guarantees to replace any quantity proved to be defective. We will not be held liable for any injury loss or change, whether direct, incidental or consequential, due to the use of or inability to use the product or due to breach of warranty of any agreement existing between Tri-Seal and the purchaser. Unless contained in this data sheet or agreed to in writing by the officers of seller and user no other warrantee will be honored.

Page 1 of 1



DeWAL INDUSTRIES

15 RAY TRAINOR DRIVE, SAUNDERSTOWN RI, 02874 USA

D/W 202

SKIVED PTFE

PRODUCT DESCRIPTION

D/W 202 is a skived PTFE (Polytetrafluoroethylene) film held to close tolerance on width and thickness. D/W 202 conforms to ASTM D3308 Type II and SAE AMS 3662C

APPLICATION INFORMATION

D/W 202 finds use in electrical applications where high temperature service rating and superior electrical properties are desired. Examples of electrical applications include capacitor films, harnesses for electrical wiring in automotive and aerospace applications, spacers for transformers and other electrical insulation applications where high dielectric strength and high temperature resistance are requisite.

TECHNICAL DATA

PROPERTY	TEST METHOD	DATA
	TEST HERIOD	PTFE Film
Backing Material	ACTM D 003	6000
Tensile Strength (psi)	ASTM-D 882	
Elongation (%)	ASTM-D 882	325
Dielectric Strength (Volts)	ASTM-D 149	2000
Max. Operating Temp. (F)		500
AVAILABILITY		
Core I.D.	3"	
Width (in)	.25-11	
Thickness (mils)	.001090	
Max Roll O.D. (in)	14	

^{*}The above values are "Typical Values" which have a nominal range about them and are not intended for specification purposes. DeWAL requests the opportunity to work with you on specifications