

HCF ^{ecccs}®

F-688/F-688'S' SPRAYABLE FOR INDUSTRIAL USE ONLY

DESCRIPTION:

HCF is a flexible acrylic, water base coating. It's very low V.O.C.'s, non-flammable and high solids content make it an Emission Control Coating System, ecccs®, that can be air dried or heat cured to meet production demands. HCF can be sprayed, dipped or brushed, is available in a wide variety of colors and exhibits excellent petroleum, chemical, UV, corrosion and abrasion resistance. Typical applications include protecting and color coding transformers, coils, tools, fixtures and brackets, oil handling equipment, heavy machinery, and chain link fence components. HCF bonds to metal, wood, concrete and plastics without primers. HCF has the safety of water base with the performance of solvent base coatings. Use HCF F-688'S' for spray applications.

SPECIFICATIONS:

Solids: (wt.)	36%
Abrasion: (ASTM D-4060)	0.0005 inches/100 cycles
Tensile: (ASTM D-2370)	1584psi
Weather ability: (ASTM G-53)	Excellent 7-10 years
Permeability:	Limited
Temperature use range:	-0°F to 250°F.
Viscosity range:	4,000-10,000cps
Finish:	Semi gloss
Shelf life:	1 year at 77°F
Coverage:	100 sq.ft. per gallon at 5 mils
Chemical resistance:	
Petroleum:	Excellent
Acid, alkaline:	Good
Alcohol, ketone, chlorinated solvent:	Limited
Ultimate elongation: (ASTM D-2370-82)	280%
Dielectric: (ASTM D-149)	1,100 v/mil

ALTERNATIVE PRODUCTS:

Contact technical service for alternatives.

DIRECTIONS: Use Adequate Ventilation. Mix Well Before Use. All surfaces to be coated must be free of all oils, grease, dirt, wax, and loose rust. A sandblasted or rough surface improves adhesion. Use PLASTI DIP® PRIMER for best results on smooth metal surfaces.

SPRAYING - F-688'S' ONLY: Pressure pot/conventional sprayers may be used. Gently mix before spraying. Apply wet, overlapping coats, holding gun 6"-12" from surface, using a 4"-6" pattern. Allow to completely dry before applying additional coats to desired thickness.

RECOMMENDED EQUIPMENT AND SETTINGS:

Gun: Binks® model 95
Nozzle: 63B
Cap: 63PB or 66SD-3 for heavier build up
Needle: 663A
Material: 25psi
Atomization: 15-25psi
Dilution: none required
Clean up: water, mild solvent if allowed to dry

Industrial/commercial airless equipment may be used. Use as described above.

Tip sizes: .011 - .019
Pressure: as needed
Dilution: as needed

DIPPING - F-688 ONLY: Gently mix before each use. Do not introduce air bubbles. Insert item 1" every 5 seconds. Remove at same rate. Allow to completely dry before applying additional coats to desired thickness.

BRUSH/ROLLER - F-688 ONLY: Gently mix before each use. Apply wet overlapping coats using a foam brush, pad or roller. Allow to completely dry before applying additional coats to desired thickness.

HINTS:

For storage or dip tank containers, use only poly or galvanized steel. A dry film thickness of 6-8 mils is recommended for best results. Allow overnight drying whenever possible. To speed drying, mild heat (95°F-110°F) and air flow may be used. Do not stack or store parts in contact with each other if not fully cured. Avoid excessive air movement, heat or humidity. Always use proper ventilation and protection.

We cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the applications of this information or the safety and suitability of our products, either alone or in combination with other product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products whether used alone or in combination with other products. Ever changing V.O.C. regulations in your area may require you to contact local authorities for proper use and/or disposal of this product. Should you need further assistance, please contact PLASTI DIP INTERNATIONAL technical service.

PLASTI DIP, eccs, Performix and logo are registered trademarks of PLASTI DIP INTERNATIONAL
BINKS is a registered trademark of BINKS MFG. CO., Franklin Park, IL

TECHNICAL DATA SHEET #10
REVISED 7/11/2003DR
HCF