

Description

Lexan* 9034 uncoated polycarbonate sheet is the standard grade of Lexan sheet for transparent protective glazing. High-impact Lexan 9034 sheet may be an excellent candidate for primary glazing, or on either side of existing glazing for economical protection against breakage or intrusion. A better insulator than glass, Lexan 9034 sheet may contribute to lower energy costs.

Typical Property Values ♦

Property	Test Method	Unit	Value
Physical			
Specific Gravity	ASTM D792	—	1.20
Refractive Index @ 77°F	ASTM D542A	—	1.586
Light Transmission (Average), 1/8" disk	ASTM D1003	%	88
Rockwell Hardness	ASTM D785	—	M70
Abrasion Resistance, Taber Abrader, CS-17 wheel	ASTM D1044	mg/1,000 cycles	10
Water Absorption, Equilibrium, 24 hrs	ASTM D570	%	0.15
@ 73°F			0.35
@ 212°F			0.58
Mechanical			
Tensile Strength @ Yield	ASTM D638	psi	9,000
@ Ultimate			9,500
Tensile Modulus	ASTM D638	psi	345,000
Flexural Strength	ASTM D790	psi	13,500
Flexural Modulus	ASTM D790	psi	345,000
Flexural Endurance @ 1,800 cycles/min, 73°F, 50% RH	ASTM D671	psi	1,000
Compressive Strength	ASTM D695	psi	12,500
Compressive Modulus	ASTM D695	psi	345,000
Elongation	ASTM D638	%	110
Poisson's Ratio	—	—	0.37
Izod Impact Strength Notched @ 1/8"	ASTM D256A	ft-lbs/in	12–16
Unnotched @ 1/8"			60 (no failure)
Tensile Impact Strength, S-Type Specimen	ASTM 1822	ft-lbs/in ²	225–300
Shear Strength @ Yield	ASTM D732	psi	6,000
@ Ultimate			10,000
Shear Modulus	ASTM D732	psi	114,000
Deformation Under Load @ 4,000 psi @ 73°F	ASTM D621	%	0.2
@ 158°F			0.3
Thermal			
Coefficient of Thermal Expansion	ASTM D696	in/in/°F	3.75 x 10 ⁻⁵
Coefficient of Thermal Conductivity	ASTM C177	Btu•in/hr•ft ² •°F	1.35
Specific Heat @ 40°C		cal/gm/°C	0.30
Heat Deflection Temperature @ 264 psi	ASTM D648	°F	270
@ 66 psi			280
Brittle Temperature	ASTM D746	°F	211
Flammability			
Horizontal Burn (Flame Spread) AEB	ASTM D635	in	<1
Electrical			
Dielectric Constant @ 10 Hz	ASTM D150	—	2.96
@ 60 Hz			3.17
Volume Resistivity	ASTM D257	ohm-cm	8.2 x 10 ¹⁶
Power Factor @ 60 Hz	ASTM D150		0.0009
@ 1,000,000 Hz			0.010
Arc Resistance	ASTM D495	sec	
Stainless Steel Strip Electrodes			10–11
Tungsten Electrodes			120

♦ These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local SABIC Innovative Plastics representative or SABIC Innovative Plastics Quality Services Department.

* Trademarks of SABIC Innovative Plastics IP BV



* Trademark of SABIC Innovative Plastics IP BV

Americas:

SABIC Innovative Plastics
Specialty Film & Sheet
One Plastics Avenue
Pittsfield, MA 01201
USA
Tel. (1) (413) 448 5400
Fax. (1) (413) 448 7506
Toll free: 1-800 451 3147

Europe:

SABIC Innovative Plastics
Specialty Film & Sheet
Plasticslaan 1
NL - 4612 PX Bergen op Zoom
The Netherlands
Tel. (31) (164) 292911
Fax. (31) (164) 293272

Pacific:

SABIC Innovative Plastics
Specialty Film & Sheet
1266 Nanjin Road (W)
Plaza 66, 17th Floor
200040 Shanghai, China
Tel. (86) 21 62881088
Fax. (86) 21 62880818

THE MATERIALS, PRODUCTS AND SERVICES OF SABIC INNOVATIVE PLASTICS HOLDING BV, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH CAN BE FOUND AT <http://www.sabic-ip.com> AND ARE AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION OR RECOMMENDATION CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SELLER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SELLER'S PRODUCTS, SERVICES OR RECOMMENDATIONS. EXCEPT AS PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. No statement by Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC Innovative Plastics is a trademark of Sabic Holding Europe BV

* Trademark of SABIC Innovative Plastics IP BV